

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C09B 67/22, D21H 21/28	A1	(11) International Publication Number: WO 00/61689 (43) International Publication Date: 19 October 2000 (19.10.00)
(21) International Application Number: PCT/EP00/02955 (22) International Filing Date: 3 April 2000 (03.04.00) (30) Priority Data: 9907878.4 8 April 1999 (08.04.99) GB (71) Applicants (for all designated States except US): CIBA SPECIALTY CHEMICALS HOLDING INC. [CH/CH]; Klybeckstrasse 141, CH-4057 Basel (CH). STORA KOPPARBERGS BERGSLAGS AB [SE/SE]; S-791 80 Falun (SE). (72) Inventors; and (75) Inventors/Applicants (for US only): KNOWLES, Ian, William [GB/GB]; 267 Broadstone Road, Heaton Chapel, Stockport, Cheshire SK4 5HH (GB). WATSFELDT, Robert [SE/SE]; Valebergsvagen 4c, S-427 37 Billdal (SE). KUMLIN, Kjell, Erik [SE/SE]; Fågelsångsvägen 18, S-652 30 Karlstad (SE). (74) Common Representative: CIBA SPECIALTY CHEMICALS HOLDING INC.; Patentabteilung, Klybeckstrasse 141, CH-4057 Basel (CH).		(81) Designated States: AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: PIGMENT COMPOSITIONS AND PROCESS OF SHADING		
(57) Abstract Compositions comprising a) a mixture of i) C.I. Pigment Violet 19 together with either C.I. Pigment Blue 15 or C.I. Pigment Blue 60, or ii) C.I. Pigment Red 177 together with either C.I. Pigment Blue 15 or C.I. Pigment Blue 60, and b) a dispersant, c) optionally a biocide, and d) water. A process for shading of paper using said compositions or by applying separate pigment dispersions of a) C.I. Pigment Violet 19 and either C.I. Pigment Blue 15 or C.I. Pigment Blue 60, or b) C.I. Pigment Red 177 and either C.I. Pigment Blue 15 or C.I. Pigment Blue 60.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

PIGMENT COMPOSITIONS AND PROCESS OF SHADING

The present invention relates to compositions comprising special pigments which meet BGVV specifications for food packaging materials.

It is the object of the present invention to provide a pigment composition which can be used for the shading of food packaging materials, especially such materials which are made of paper.

In one aspect, the invention relates to a composition comprising

- a) a mixture of C.I. Pigment Violet 19 together with either C.I. Pigment Blue 15 or C.I. Pigment Blue 60,
- b) a dispersant,
- c) optionally a biocide, and
- d) water.

One preferred form of this composition comprises a mixture of C.I. Pigment Violet 19 together with C.I. Pigment Blue 15, in which mixture the amount by weight of C.I. Pigment Violet 19 is greater than 50%, based on the weight of the mixture of pigments. The mixture of pigments contains usually 60% to 95% by weight, preferably 70% to 90% by weight, of C.I. Pigment Violet 19, based on the weight of the mixture of pigments. Particularly preferred are compositions wherein the mixture of pigments contains 75% to 85 % by weight of C.I. Pigment Violet 19 and 15% to 25 % by weight of C.I. Pigment Blue 15.

A further preferred form of this composition comprises a mixture of C.I. Pigment Violet 19 together with C.I. Pigment Blue 15 or C.I. Pigment Blue 60, in which mixture the amount by weight of C.I. Pigment Violet 19 is less than 50%, based on the weight of the mixture of pigments. Particularly preferred compositions comprise a mixture of pigments containing C.I. Pigment Violet 19 together with C.I. Pigment Blue 60. The mixture of pigments contains usually 30% to less than 50 % by weight, preferably

40% to less than 50 % by weight of C.I. Pigment Violet 19, based on the weight of the mixture of pigments.

In a second aspect, this invention relates to a composition comprising

- a) a mixture of C.I. Pigment Red 177 together with C.I. Pigment Blue 15 or C.I. Pigment Blue 60,
- b) a dispersant,
- c) optionally a biocide, and
- d) water.

Particularly preferred are compositions that include a mixture of pigments containing C.I. Pigment Red 177 together with C.I. Pigment Blue 60. The mixture of pigments contains usually below 60 % by weight, preferably below 50 % by weight of C.I. Pigment Red 177, based on the weight of the mixture of pigments. Highly preferred are mixtures of pigments which contain 20 or 25 to 40 % by weight of C.I. Pigment Red 177 and 60 to 75 % by weight of C.I. Pigment Blue 60.

The compositions in all aspects of the invention contain preferably 0.1 to 40%, more preferably 10 to 30 % of pigments, most preferably around 20% of pigments, based on the weight of the composition.

The size of the pigments can range from a few nanometres to several hundreds of microns. Preferred is an average size distribution of 0.01 to 1 micron.

The dispersant usually is present in the composition in an amount of 0.1 to 30%, preferably 0.1 to 8% by weight, most preferably 3 to 6%, based on the weight of the composition.

Preferred dispersants are for example polyacrylic acid, polymethacrylic acid, polymaleic anhydride, polyurethane, polyvinylether, polyvinylalcohol, polyalkylene glycol, polyethylene oxide, cellulose derivatives, polyimine, polyvinylpyridine, or

copolymers thereof, or copolymers such as copolymers of acrylic acid with styrene, acrylonitrile, vinylacetate, vinylphosphonate, vinylpropionate, vinylchloride, itaconic acid or maleic anhydride, or a mixture thereof. Suitable polymeric derivatives are for example ethoxylated or propoxylated fatty amines such as ethoxylated cocoalkyl, oleyl or soyaalkyl amines; ethoxylated or propoxylated fatty quaternary salts such as ethoxylated cocoalkyltrimethyl ammonium chloride; ethoxylated fatty amides such as ethoxylated oleamides; alkyl-, cycloalkyl- or alkylaryl-oxypoly(ethylenoxy)ethanol, cycloalkyloxypoly(ethylenoxy)laurate or oleate, polyethylene glycol 400 laurate or oleate, alkyl-, cycloalkyl- or alkylaryl-poly(ethylenoxy)carboxylate or phosphonate. An especially preferred cycloalkyloxypoly(ethylenoxy) laurate or oleate is for example a poly(ethylenoxy)sorbitan laurate or oleate. Particularly preferred dispersants include polymers of aromatic sulphonic acids with formaldehyde, and salts thereof. Typically the dispersants have molecular weights in the range 1000 to 10,000, preferably 2,000 to 5,000, especially 2,500 to 3,500. These preferably water-soluble polymers, copolymers and/or polymer derivatives are known per se and are commercially available.

Preferably, the compositions contain a biocide. All FDA and BGVV compliant biocides are suitable for this application. Any of such biocide capable of inhibiting the growth of either or all of Gram positive or Gram negative bacteria, yeasts or fungi may be employed according to the present invention. Suitable biocides include thiazol-3-one derivatives, for instance alkyl and/or chlorinated derivatives of thiazol-3-one or mixtures thereof. Typically the biocide is present at levels of from about 15 parts per million (ppm) by weight of the composition to about 1000 ppm, most preferably from about 50 ppm to about 500 ppm by weight of the composition.

A further object of the present invention is to provide a process for the shading of paper wherein either of the above compositions or separate dispersions of said constituent pigments are applied to at least one stage of the paper making process.

Thus one aspect of the invention relates to a process for shading of paper to be used for food packaging material, which process comprises applying to at least one stage of the paper making process either

a) a composition comprising

- i) a mixture of C.I. Pigment Violet 19 together with C.I. Pigment Blue 15,
- ii) a dispersant,
- iii) optionally a biocide, and
- iv) water.

or

b) an aqueous dispersion of C.I. Pigment Violet 19 and an aqueous dispersion of C.I. Pigment Blue 15.

The aqueous pigment dispersions of C.I. Pigment Violet 19 comprises,

- a) C.I. Pigment Violet 19,
- b) a dispersant,
- c) optionally a biocide, and
- d) water.

The aqueous pigment dispersion of C.I. Pigment Blue 15 comprises,

- a) C.I. Pigment Blue 15,
- b) a dispersant,
- c) optionally a biocide, and
- d) water.

The preferences given before for the compositions also apply to the process for applying the compositions.

In one preferred form of the process of shading paper, a dispersion of C.I. Pigment Violet 19 and a dispersion of C.I. Pigment Blue 15 are applied to at least one stage of the paper making process, wherein the C.I. Pigment 19 is added in an amount of greater than 50% by weight of added pigments. The C.I. Pigment 19 is usually added

in an amount of 60% to 95% by weight, preferably 70% to 90% by weight of the added pigments. In a particularly preferred form of the process C.I. Pigment Violet 19 is added in an amount of 75% to 85 % by weight and C.I. Pigment Blue 15 is added in an amount of 15% to 25 % by weight of C.I. Pigment Blue 15 based on the weight of the added pigments.

In another preferred form of the process a dispersion of C.I. Pigment Violet 19 and a dispersion of either C.I. Pigment Blue 15 or C.I. Pigment Blue 60 are added to at least one stage of the paper making process, wherein amount of C.I. Pigment Violet 19 used is less than 50% of the total amount of pigment used. The amount of C.I. Pigment Violet 19 used is usually 30% to less than 50 % by weight, preferably 40% to less than 50 % by weight, based on the weight of the pigments used.

A further aspect of the process of the invention relates to a process for shading of paper to be used for food packaging material, which process comprises applying at least one stage of the paper making process either

a) a composition comprising,

- i) a mixture of C.I. Pigment Red 177 together with C.I. Pigment Blue 15 or C.I. Pigment Blue 60,
- ii) a dispersant,
- iii) optionally a biocide, and
- iv) water,

or

b) an aqueous dispersion of C.I. Pigment Red 177 and an aqueous dispersion of either C.I. Pigment Blue 15 or C.I. Pigment Blue 60.

The aqueous pigment dispersions of C.I. Pigment Red 177 comprises,

- a) C.I. Pigment Red 177,
- b) a dispersant,
- c) optionally a biocide, and
- d) water.

The aqueous pigment dispersion of C.I. Pigment Blue 15 or C.I. Pigment Blue 60 comprises,

- a) C.I. Pigment Blue 15 or C.I. Pigment Blue 60,
- b) a dispersant,
- c) optionally a biocide, and
- d) water.

In the process of shading paper in which a dispersion of C.I. Pigment Red 177 and a dispersion of either C.I. Pigment Blue 60 or C.I. Pigment Blue 15 is added to at least one stage of the paper making process, C.I. Pigment Red 177 is usually added in an amount below 60 % by weight, preferably below 50% by weight, of the added pigments. In a particularly preferred process C.I. Pigment Red 177 is added in an amount of 20 or 25 to 40 % by weight, based on the weight of added pigments and C.I. Pigment Blue 15 or C.I. Pigment Blue 60 is added in an amount of 60 to 75 % by weight of the added pigments.

When separate pigment dispersions are applied to the process it is possible for the aqueous pigment dispersions to be added at different stages of the paper making process, though best results are usually obtained if the pigment dispersions are added to the same stage. As for the combined pigment compositions the separate aqueous pigment dispersions contain preferably 0.1 to 40%, more preferably 10 to 30%, most preferably around 20% of the respective pigment, based on the weight of the dispersion. Generally the amounts of dispersants and biocides used in each of the aqueous pigment dispersions would be substantially the same as the amounts used in the composition given before.

According to conventional paper making processes the pulp is processed in a mixing chest where it is mixed in a conventional manner to form a thick stock, which is then diluted to form the thin stock, the thin stock is passed towards a drainage screen through various items of apparatus such as a fan pump and a centri screen, and the

thin stock is drained through a screen so as to form a sheet, which is then dried. Such conventional processes are described, for example, in US-A-5,676,796.

For example, the composition can be added to the pulp, the mixing chest, the thick stock or the thin stock.

Whether the pigments are added in the form of the composition or in the form of separate pigment dispersions they are as a rule added in an amount of 5 to 1000 g per tonne, preferably in an amount of 10 to 400 g/tonne and most preferably in an amount of 50 or 100 to 400 g/tonne. The gram hereby refers to equivalent total dry weight of pigment added and the tonne hereby refers to the equivalent dry weight of material the composition or pigment dispersions are added to (for example the pulp).

In addition, at one of the stages of the paper making process a cationic coagulant or cationic retention aid can be added.

Preferably, the cationic coagulant is added prior to dilution, most preferably to the thick stock.

The coagulant usually is added in an amount of 10 to 1000 g/tonne, preferably in an amount of 50 to 700 g/tonne and most preferably in an amount of 100 to 500 g/tonne. The tonne hereby refers to the material the composition is added to (for example the thick stock).

Typical examples of coagulants are polyamine epichlorohydrin, polyethylene imine, polymers of cationic monomers such as diallyl dimethyl ammonium chloride, dialkyl aminoalkyl (meth)acrylates or quaternary ammonium salts, dialkyl aminoalkyl (meth)acrylamides or quaternary ammonium salts. Preferred are coagulants which have an intrinsic viscosity (IV) of below 3 dl/g and a cationic charge density of at least 4 meq/g.

The cationic retention aid may be the same polymer as the cationic coagulant or more usually is either cationic starch or a copolymer of cationic monomers such as diallyl dimethyl ammonium chloride, dialkyl aminoalkyl (meth)acrylates or quaternary ammonium salts, dialkyl aminoalkyl (meth)acrylamides or quaternary ammonium salts with nonionic monomers such as acrylamide. Typically the cationic retention aids are synthetic polymers which have an intrinsic viscosity (IV) of at least 3dl/g, usually at least 4 or 5 dl/g and can be as high as 10 or 12 dl/g or higher. Typically the cationic retention aids can have a cationic charge density of below 4 meq/g, preferably below 3 meq/g,

Another object of the present invention is the use of the inventive composition for shading of paper to be used for food packaging material.

The paper may be filled or unfilled paper and may be lightweight or heavyweight. The paper may be, for instance, paper board.

The special combination of pigments used according to the present invention allows shading of food packaging materials in a good manner. Especially for paper materials a very good whiteness is obtained.

These dispersions are suited for direct food contact packaging, eliminating the need for overwrapping foods. (Color additive petition for paper and board is pending.) The food can be in liquid form as well as in solid form.

Furthermore, the dispersions are stable for a longer period of time and can therefore be stored before application, without showing deposits resulting in deteriorous application properties.

The following examples illustrate various embodiments of the invention, but the scope of the invention is not limited thereto. In the examples, percentages are by weight, unless otherwise indicated.

Example 1:

By mixing the following dispersion is prepared:

16 wt% C.I. Pigment Violet 19

4 wt% C.I. Pigment Blue 15

5.6 wt% 2-naphthalene sulphonic acid polymer with formaldehyde, sodium salt

0.008 wt% 5-chloro-2-methyl-2H-isothiazol-3-one

0.003 wt% 2-methyl- 2H-isothiazol-3-one.

74.389 wt% water

Examples 2 to 5:

To a pulp comprising an elemental chlorine free blend of 70% bleached hardwood and 30% bleached softwood, 10% by weight of a filler (calcium carbonate) and 1.5% of a conventional sizing agent (Keydime C), the pulp having a pH of about 7.2, are added the dispersions given in the following Table 1 (the amounts given in Table 1 are given in % by weight, based on the weight of the pulp):

Table 1

Example	Amount of the dispersion of Example 1 (based on the weight of the pulp)
2	100 g/tonne
3	200 g/tonne
4	300 g/tonne
5	500 g/tonne

The pulp is processed further according to conventional methods, which means in the mixing chest the pulp is mixed in a conventional manner to form a thick stock, which is then diluted to form the thin stock, the thin stock is passed towards a drainage screen through various items of apparatus such as a fan pump and a centri screen, and draining the thin stock through a screen so as to form a sheet, which is then dried. In each case a paper is obtained which shows very good whiteness.

Example 6:

The above Example 4 is repeated, except that just prior to diluting the thick stock 300 g/tonne of a coagulant (Nalco 7607) is added. A paper is obtained which shows very good whiteness.

Example 7:

By mixing the dispersions given in the following Table 2 are prepared:

Table 2

Dispersion	Violet Pigment	Blue Pigment	Dispersant	*Biocide	Water
A1	9.8 % of C.I. Pigment Violet 19	10.2 % of C.I. Pigment Blue 60	5.6 % of 2- naphthalene sulphonic acid polymer with formaldehyde, sodium salt	0.008 % of CMITO and 0.003 % of MITO	Water made up to 100%
B1	4.9 % of C.I. Pigment Violet 19	5.1 % of C.I. Pigment Blue 15	5.6 % of 2- naphthalene sulphonic acid polymer with formaldehyde, sodium salt	0.008 % of CMITO and 0.003 % of MITO	Water made up to 100%

*The biocide CMITO is 5-chloro-2-methyl-2H-isothiazol-3-one and MITO is 2-methyl-2H-isothiazol-3-one.

Examples 8 to 15:

To a pulp comprising an elemental chlorine free blend of 70% bleached hardwood and 30% bleached softwood, 10% by weight of a filler (calcium carbonate) and 1.5%

of a conventional sizing agent (Keydime C), the pulp having a pH of about 7.2, are added the dispersions given in the following Table 2 (the amounts given in Table 2 are given in % by weight, based on the weight of the pulp):

Table 3

Example	Dispersion	Amount of the dispersion based on the weight of the pulp
8	A1	100 g/tonne
9	A1	200 g/tonne
10	A1	300 g/tonne
11	A1	500 g/tonne
12	B1	100 g/tonne
13	B1	200 g/tonne
14	B1	300 g/tonne
15	B1	500 g/tonne

The pulp is processed further according to conventional methods, which means in the mixing chest the pulp is mixed in a conventional manner to form a thick stock, which is then diluted to form the thin stock, the thin stock is passed towards a drainage screen through various items of apparatus such as a fan pump and a centri screen, and draining the thin stock through a screen so as to form a sheet, which is then dried. In each case a paper is obtained which shows very good whiteness.

Examples 16 and 17:

Each of the above Examples 10 and 14 are repeated, except that just prior to diluting the thick stock 300 g/tonne of a coagulant (Nalco 7607) is added. In each case a paper is obtained which shows very good whiteness.

Example 18:

By mixing the following dispersions of C.I. Pigment Red 177, C.I. Pigment Blue 15 and Pigment Blue 60 are prepared:

C.I. Pigment Red 177 Dispersion

19.9%	C.I. Pigment Red 177
4.0%	2-Naphthalene sulphonic acid, polymer with formaldehyde, sodium salt
0.008%	5-Chloro-2-methyl-2H-isothiazol-3-one
0.003%	2-Methyl-2H-isothiazol-3-one
79.089%	Water

C.I. Pigment Blue 60 Dispersion

19.6%	C.I. Pigment Blue 60
5.74%	2-Naphthalene sulphonic acid, polymer with formaldehyde, sodium salt
0.008%	5-Chloro-2-methyl-2H-isothiazol-3-one
0.003%	2-Methyl-2H-isothiazol-3-one
79.649%	Water

C.I. Pigment Blue 15 Dispersion

18.50%	C.I. Pigment Blue 15
5.60%	2-Naphthalene sulphonic acid, polymer with formaldehyde, sodium salt
0.008%	5-Chloro-2-methyl-2H-isothiazol-3-one
0.003%	2-Methyl-2H-isothiazol-3-one
75.889%	Water

Examples 19 to 22:

To a thick stock comprising an elemental chlorine free blend of 70% bleached hardwood and 30% bleached softwood, 10% by weight of a filler (calcium carbonate) and 1.5% of a conventional sizing agent (Keydime C), the pulp having a pH of about

7.2, pigment dispersions are added to the thick stock at doses given in Table 4 based .

Table 4

Example	C.I. Pigment Red177 Dispersion	C.I. Pigment Blue 60 Disperison	C.I. Pigment Blue 15 Disperion
19	60 g/ tonne	200 g/tonne	-
20	20g/tonne	66 g/tonne	-
21	6g/tonne	20 g/tonne	-
22	114g/tonne	-	86g/tonne

The pulp is processed further according to conventional methods, which means in the mixing chest the pulp is mixed in a conventional manner to form a thick stock, which is then diluted to form the thin stock, the thin stock is passed towards a drainage screen through various items of apparatus such as a fan pump and a centri screen, and draining the thin stock through a screen so as to form a sheet, which is then dried. In each case a paper is obtained which shows very good whiteness.

Examples 23 and 24:

Each of the above Examples 19 and 22 is repeated, except that just prior to diluting the thick stock 300 g/tonne of a coagulant (Nalco 7607) is added. In each case a paper is obtained which shows very good whiteness.

Claims

1. A composition comprising

- a) a mixture of C.I. Pigment Violet 19 together with either C.I. Pigment Blue 15 or C.I. Pigment Blue 60,**
- b) a dispersant,**
- c) optionally a biocide, and**
- d) water.**

2. A composition according to claim 1 wherein component a) comprises a mixture of C.I. Pigment Violet 19 together with C.I. Pigment Blue 15, in which mixture the amount by weight of C.I. Pigment Violet 19 is greater than 50%, based on the weight of the mixture of pigments.

3. A composition according to claim 1 or claim 2, wherein the mixture of pigments contains 60% to 95% by weight of C.I. Pigment Violet 19.

4. A composition according to any one of claims 1 to 3, wherein the mixture of pigments contains 70% to 90% by weight of C.I. Pigment Violet 19.

5. A composition according to any one of claims 1 to 4, wherein the mixture of pigments contains 75% to 85% by weight of C.I. Pigment Violet 19 and 15% to 25% by weight of C.I. Pigment Blue 15.

6. A composition according to claim 1 wherein component a) comprises a mixture of C.I. Pigment Violet 19 together with C.I. Pigment Blue 15 or C.I. Pigment Blue 60, in which mixture the amount by weight of C.I. Pigment Violet 19 is less than 50%, based on the weight of the mixture of pigments,

7. A composition according to claim 6, wherein the mixture of pigments contains C.I. Pigment Violet 19 together with C.I. Pigment Blue 60.

8. A composition according to claim 6 or claim 7, wherein the mixture of pigments contains 30% to less than 50 % by weight of C.I. Pigment Violet 19.

9. A composition according to any one of claim 6 to claim 8, wherein the mixture of pigments contains 40% to less than 50 % by weight of C.I. Pigment Violet 19.

10. A composition comprising

- a) a mixture of C.I. Pigment Red 177 together with C.I. Pigment Blue 15 or C.I. Pigment Blue 60,
- b) a dispersant,
- c) optionally a biocide, and
- d) water.

11. A composition according to claim 10, wherein the mixture of pigments contains C.I. Pigment Red 177 together with C.I. Pigment Blue 60.

12. A composition according to claim 10 or claim 11, wherein the mixture of pigments contains below 60 % by weight of C.I. Pigment Red 177.

13. A composition according to any one of claims 10 to 12, wherein the mixture of pigments contains below 50 % by weight of C.I. Pigment Red 177.

14. A composition according to any one of claims 5 to 8, wherein

the mixture of pigments contains 20 to 40 % by weight of C.I. Pigment Red 177 and 60 to 75 % by weight of C.I. Pigment Blue 60.

15. A composition according to any one of claims 1 to 14, which contains 0.1 to 40%, more preferably 10 to 30 %, most preferably around 20% pigment, based on the weight of the dispersion.

16. A composition according to any one of claims 1 to 15, which contains 0.1 to 30%, preferably 0.1 to 8% of dispersant, by weight of the composition.

17. A composition according to any one of claims 1 to 16, which contains a biocide.

18. A composition according to any one of claims 1 to 17, wherein the dispersant is polyacrylic acid, polymethacrylic acid, polymaleic anhydride, polyurethane, polyvinylether, polyvinylalcohol, polyalkylene glycol, polyethylene oxide, cellulose derivatives, polyimine, polyvinylpyridine, or copolymers thereof, or copolymers of acrylic acid with styrene, acrylonitrile, vinylacetate, vinylphosphonate, vinylpropionate, vinylchloride, itaconic acid or maleic anhydride, or ethoxylated or propoxylated fatty, ethoxylated or propoxylated fatty quaternary salts, ethoxylated fatty amides, alkyl-, cycloalkyl- or alkylaryl-oxypoly(ethylenoxy)ethanol, cycloalkyloxypoly(ethylenoxy)laurate or oleate, polyethylene glycol 400 laurate or oleate, alkyl-, cycloalkyl- or alkylaryl-poly(ethylenoxy)carboxylate or phosphonate or aromatic sulphonic acid polymer with formaldehyde or salts thereof.

19. A process for shading of paper to be used for food packaging material, which process comprises applying to at least one stage of the paper making process either

- a) a composition according to claim 1,
- b) a composition according to claim 10,
- c) an aqueous dispersion of C.I. Pigment Violet 19 and an aqueous dispersion of C.I. Pigment Blue 15, wherein amount of C.I. Pigment Violet 19, or

d) an aqueous dispersion of C.I. Pigment Red 177 and an aqueous dispersion of either C.I. Pigment Blue 15 or C.I. Pigment Blue 60.

20. A process according to claim 19, wherein the composition is added to the mixing chest, the thin stock, the thick stock or preferably to the pulp.

21. A process according to claim 19 or claim 20, wherein the composition is added in an amount of 5 to 1000 g per tonne, preferably in an amount of 10 to 400 g/tonne and most preferably in an amount of 50 to 400 g/tonne.

22. A process according to any one of claims 19 to 21, wherein in addition a cationic coagulant or retention aid is added.

23. A process according to claim 22, wherein the cationic coagulant is added to the thick stock, preferably prior to dilution.

24. A process according to claim 23, wherein the cationic coagulant is added in an amount of 10 to 1000 g per tonne, preferably in an amount of 50 to 700 g/tonne and most preferably in an amount of 100 to 500 g/tonne.

25. Use of a composition according to claim 1 or claim 10 for shading of paper to be used for food packaging material.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 00/02955

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C09B67/22 D21H21/28

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 D21H C09B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	US 6 033 444 A (AHLINDER BERTIL) 7 March 2000 (2000-03-07)	1-5
Y	the whole document	1-25
Y	US 2 844 485 A (W.S. STRUVE) 22 July 1958 (1958-07-22) column 3, line 46 - line 60	1-9, 15-25
Y	US 5 131 981 A (HENNING GEORG ET AL) 21 July 1992 (1992-07-21) column 5, line 5 - line 17	1-25
Y	EP 0 632 108 A (BASF AG) 4 January 1995 (1995-01-04) abstract page 3, line 50 - line 52	1-25
-/--		



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

18 July 2000

Date of mailing of the international search report

25/07/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Dauksch, H

INTERNATIONAL SEARCH REPORT

Inter: nal Application No

PCT/EP 00/02955

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 0 654 506 A (CIBA GEIGY AG) 24 May 1995 (1995-05-24) abstract page 9, line 35 -page 10, line 12 page 6, line 12 - line 18 ---	1-14
Y	FR 2 084 891 A (KOEGE KEMISK VAERK) 17 December 1971 (1971-12-17) page 1, line 3 - line 23 ---	1-25
A	US 3 074 950 A (W. S. STRUVE) 22 January 1963 (1963-01-22) column 2, line 29 - line 51; examples 13,15 ---	1-9, 15-25
A	FR 941 218 A (AMERICAN CYANAMID CO.) 18 January 1949 (1949-01-18) the whole document ---	10-14
A	GB 2 071 683 A (TOYO INK MFG CO) 23 September 1981 (1981-09-23) abstract page 10, line 1 - line 6 page 4, line 6 -page 6, last line -----	1-25

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 00/02955

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 6033444 A	07-03-2000	SE 9703667 A	10-04-1999
US 2844485 A	22-07-1958	NONE	
US 5131981 A	21-07-1992	DE 3732981 A	13-04-1989
		AU 2295788 A	06-04-1989
		CA 1302022 A	02-06-1992
		DE 3889049 D	19-05-1994
		DK 544388 A	31-03-1989
		EP 0309908 A	05-04-1989
		FI 884421 A, B,	31-03-1989
		JP 1104898 A	21-04-1989
EP 0632108 A	04-01-1995	DE 4321693 A	12-01-1995
		JP 7033998 A	03-02-1995
EP 0654506 A	24-05-1995	CA 2135596 A	23-05-1995
		DE 59409353 D	21-06-2000
		JP 7196939 A	01-08-1995
		US 5518539 A	21-05-1996
FR 2084891 A	17-12-1971	DK 131789 B	01-09-1975
		CH 547341 A	29-03-1974
		DE 2110999 A	07-10-1971
		GB 1348571 A	20-03-1974
		NL 7103717 A	22-09-1971
US 3074950 A	22-01-1963	NONE	
FR 941218 A	18-01-1949	NONE	
GB 2071683 A	23-09-1981	JP 1034268 B	18-07-1989
		JP 1548321 C	09-03-1990
		JP 56118462 A	17-09-1981
		DE 3106906 A	14-01-1982
		US 4310359 A	12-01-1982